

Benefits

- Superior optical clarity
- Pristine whites and vibrant colors
- Durability and damage resistance
- Thin and lightweight
- Greater impact resistance

Properties

Standard glass thickness	2.0 mm Others available upon request
Standard tolerances	Length and width: ± 0.5 mm Thickness: ± 0.05 mm
Weight	4.88 kg/m ² at 2.0 mm
Chemical strengthening Compressive stress (typical) Depth of layer (typical)	> 680 MPa > 40 μ m
Standards testing	With qualified panel backer, meets US standards for indoor use including:: <ul style="list-style-type: none">• CPSC 16• CFR 1201• ANSI Z97.1-2009• ASTM E84• ANSI maximum impact Class A• CPSC maximum impact level Cat II
Standard edge profile	Pencil

For information regarding sizing, please contact: occonnorka@corning.com



CORNING

For more information: www.corning.com/interiorarchitecture
Corning and Gorilla are registered trademarks of Corning Incorporated,
Corning, N.Y., USA