

## **Dimensional Specifications**

All requirements and criteria applicable to dimensional characteristics are summarized in Table 1.

Sample size according to ISO 2859 unless specified otherwise. Reference volume = 1 pallet.

**Table 1.** Summary of criteria applicable to dimensional characteristics.

Requirement	Definition	Unit Defect Spec/Limit		AQL	Remarks	
Outer Diameter	OD <sub>AVG</sub>	Defective if there is a 60 mm section out of the tolerance over the entire length			Standard tolerances, see Standard Dimensions	
Circularity	$NCR = \frac{1}{2} (OD_{max} - OD_{min})$	OD Range (mm)		Limit for NCR		
		< 25.0		0.3% of OD <sub>nom</sub>	Cum	
		25.0 - 35.0		0.5% of OD <sub>nom</sub>		
Wall Thickness	$WT_{AVG}$	Defective if there is a 60 mm section out of the tolerance over the entire length		Cumulative AQL of 0.25	Standard tolerances, see Standard Dimensions	
Wall Siding (LOP)	$WS = WT_{max} - WT_{min}$	Maximum siding value is 6% of the nominal wall thickness				
Length	L <sub>max</sub>	Defective if overall length is out of tolerance			Standard tolerances, see Standard Dimensions	
Bow	B <sub>center</sub>	Defective if greater than 0.7 mm			Over a 1000 mm length	
Square Cut	SC	OD Range (mm)		Limit for NCR		
		< 25.0		Not to exceed 8% OD <sub>nom</sub>	2.5	
		≥ 25.0		Not to exceed 2.0 mm		
Glazing	GID <sub>max</sub> as a percentage of OD <sub>nom</sub>	Light	Sharp edges rounded with a minimum turn in		0.65	May be specified differently on the two tube ends
		Medium	80 - 90% of OD <sub>nom</sub>			
		Heavy	65 - 7	75% of OD <sub>nom</sub>		

**NOTE**: OD, WT, NCR, and WS measurements are to be taken on the usable length of the tube. Any local deviation in each that corresponds with knots or stones or other dimensionally relevant visual characteristic shall not be evaluated with respect to the dimensional specification, but rather according to the relevant visual specification.

# **Visual Quality Specifications**

Requirements applicable to visual characteristics are summarized in Table 2.

Sample size according to ISO 2859 unless specified otherwise. Reference volume = 1 pallet.

**Table 2.** Summary requirements applicable to visual characteristics.

Requirement	Detail/Parameter	Individual Defect Definition	AQL	Remarks	
Airlines	Single	L > 150 mm or W ≥ 0.08 mm	0.4	Defective if any airline in the tube exceeds limit Length or Width.	
	Aggregate length of airlines	Aggregate length of airlines L > 30 mm and W > 0.02 mm	≤ 7.5 %	As a percentage of tested tubing length. Apply to both open and closed airlines.	
Inclusions	Size (S)/count	Defective if inclusion count per 5 kg tubing exceeds the following limits.  Size (mm) Count		Inclusions up to 0.5 mm are not considered defects.  AQL not specified; 5 kg tubing must be controlled.	
		S ≥ 0.8 0 allowed per 5 kg S ≥ 0.5 Max 8 allowed per 5 kg			
Glass Particles	Size (S)/count	Defective if the following maximum allowed numbers of glass particles is exceeded.		Glass particles up to 0.2 mm are not considered defects.	
		OD Range (mm)     S ≥ 0.5     S ≥ 0.2       < 15.0	0.4		
Cracks	Surface cracks	≥ 25.0 0 10	0.025	End cracks ≤ 2 mm are not	
Cracks	Surface cracks	Any size, any length	0.023	considered defects, 20 mm from	
	End cracks	L > 2.0 mm	0.65	each side not considered defects.	
Scratches Coated Tubes	Longitudinal	W > 0.1 mm and L > 30 mm	1.0	20 mm from each side are not considered defects.  Only for bundlepack.	
	Aggregate length	W > 0.1 mm and AL > 150 mm			
	Circular	W > 0.1 mm and Arc > $\frac{1}{2}$ circumference			
Scratches Uncoated Tubes	Longitudinal	W > 0.2 mm and L > 100 mm	1.0	20 mm from each side not considered. (Applies also for all tubes in sleeve pack).	
	Aggregate length	W > 0.2 mm and AL > 300 mm			
	Circular	W > 0.2 mm and Arc > 1 circumference			
Surface Impurities	Outer surface	Defective if impurities cannot be easily removed. > 1.0 mm	0.1		
	Inner surface	> 0.5 mm	0.1		

### **Other Requirements**

Requirements for other characteristics are summarized in Table 3.

**Table 3.** Summary requirements of other characteristics.

Requirement	Detail	Defect Specification	AQL	Remarks
Residual Stress	Longitudinal	Stress > 4.0 MPa	2.5	
	Circular	Stress > 4.5 MPa		
Mix-up	Delivered articles are not uniform in the pallet	Example: different glass types, dimensions, coating level, different identification (label)	Not permissible	
Identification	Wrong Data	Incorrect identification data on bundle (e.g., declared dimensions, bundle weight, pallet weight)	Not permissible	Test unit = 1 bundle
	Missing bundle label	Missing bundle labels	Not permissible	
Certificates	Wrong or missing data	Missing certificate or pallet label	Not permissible	
Туре І	Ph. Eur. 3.2.1, Test B, USP <660 > Glass grain test	> 0.1 mL of 0.02 M HCl per 1g of glass	Not permissible	JP 7.01 Test for glass containers for injections upon request
Paneling (Waving)	Long range optical anomaly due to deviation from circularity or glass inhomogeneity	Based on agreed upon limit samples	1.0 for unprinted ampoules. 0.25 for printed ampoules.	Local deformation or inhomogeneity (e.g., knots) should not be considered a paneling defect.

#### **Standard Dimensions**

Length standard tolerance is -0.0/+4.0 mm.

**Table 4**. Defines standard OD and ID tolerances depending on the OD and ID nominal values.

OD Range (mm)	ID Range (mm)	OD Tol (mm)	ID Tol (mm)
9.0 - 14.9	0.40 - 0.55	0.12	0.02
	0.60 - 0.75	0.13	0.03
15.0 - 17.9	0.45 - 0.60	0.14	0.03
	0.65 - 0.75	0.15	0.03
18.0 - 19.9	0.55 - 0.60	0.15	0.03
	0.65 - 0.75	0.18	0.04
20.0 - 24.9	0.65 - 0.80	0.19	0.04
25.0 - 29.9	0.75 - 0.90	0.20	0.04

#### **Contact Us**

**Corning Incorporated** Life Sciences,

Pharmaceutical Technologies www.corning.com/CPT

NORTH AMERICA t +1.856.794.7100 cpginfousa@corning.com

Corning Pharmaceutical Glass, LLC Corning Pharmaceutical Glass S.p.A. t +39.050.56.66.11 cpginfoeu@corning.com

CHINESE MAINLAND **Corning Pharmaceutical** Glass Co., LTD t +86.552.3733886 cpginfoas@corning.com

Corning Technologies India Private Limited t +91.124.460.4000 Inquiriesin@corning.com